

EUROTILES PU KOTE 212 consists of acrylic copolymer emulsion with specialized elastic fiber. It can display excellent adhesion with great waterproofing ability and tensile strength. The addition of fibers in this formulation also enhances its durability, anti-cracking ability and waterproofing character.

USES

• Eurotiles PU Kote can be used on outdoor walls, G.I. roofs, concrete roof decks, balconies, gardens, restrooms and on most intermediate waterproofing constructions.

TECHNICAL DATA

TEST ITEM	TEST METHOD	TEST RESULT
Tensile Strength (kgf/cm2)	Reference ASTM D412-15a Die C 500mm/min	49.1
Elongation (%)		279
Tear Strength (kgf/cm)	Reference ASTM D624-00 (2012) Die C 500mm/min	30.6
Adhesion (1mm、100 frame)	ASTM D1308-09e2	5B
Salt water resistance (5% Sodium Chloride 230C 24hours)	ASTM D1308-02 (2013) Dipping method	No abnormality

Film Thickness	Wet film – 500 um Dry Film – 200 - 250um	
Product Viscosity	10,000 - 12,000 MPa @ 25°C	
Practical coverage	1 Gallon: 8–10 m² 5 Gallons: 56 - 60 m²	
Drying Time (25°C)	Tact- free – 1 - 2 hours Recoat - 2 - 4 hours	
Painting Interval	At least 4 hours, up to about 1 day	
Color	Gray, white and beige	
Packaging	20kg pail	
Gross Weight	5 Gallons: 21 ± 0.5 kg	
Storage	cool, dry place	
Shelf life	12 months (unopened container)	

HOW TO USE

A. Substrate Preparation •

- Remove all lose and defective paint, oil, fluid, moss or other substances on the surface. In severe
 cases, please wash the surface with water, and make sure that the surface is completely dry and
 clean. If the construction site is outdoors, please check the weather forecast before application of
 Eurotiles PU Kote 212.
 - Application tools: Foam roller, trowel, sprayer, brush

B. Surface Pre-Treatment and Primer Brushing

- If there is old PU or other waterproofing layers on the surface to be coated, remove it completely and clean it afterwards.
- The surface to be coated is to be fully repaired and filled in, including corner fill operations. If it cracks, first apply brushing primer and then coat it with thick waterproof perfusion level.

C. Top Coat Application -

- Stir thoroughly before use.
- Dilution is not recommended. If it is required, please dilute no more than 10% water.
- Primer: A minimum of one coat is required. Drying time is abut 1-2 hours.
- Top coat: A minimum of two coats is required. Re-coat time is about 2-4 hours depending on the atmospheric conditions.
- Roof deck: A minimum of 2mm thickness for the applied product is required.

PRECAUTIONS

- Do not use if rain or heavy rain dew is expected within the next 24 hours.
- Do not use where negative hydrostatic pressure is expected/present.
- Avoid applying the temperature is below 15°C (59°F).
- After the container is opened, please use the product immediately and avoid long-term storage.
- The product should be stored in a cool area, please avoid placing it directly under sunlight to prevent deterioration.
- Practical coverage is for reference only, it can differ depending on the brushing surface, flatness, and thickness.
- Drying time is for reference only, it can differ depending on the brushing thickness, humidity and the air floor condition.

DISCLAIMER: Due to different working methods, the manufacturer is not liable for any damages and faulty outcomes arising from incorrect use of this product. Please follow the instructions mentioned above.

PRODUCT MADE IN TAIWAN

Km 39 Emilio Aguinaldo Highway, Biga 2, Silang, Cavite Tel. No.: (632) 8635-2310 to 16 Fax No.: (632) 8635-2317